


PLASTIC MOLD STEEL GRADES


ROUND



FLAT



BLOCK



444 20 50  yuksele.com



Plastic Mold Steel Grades


38 Supreme

1.2738 QT HH MOD

Choice Of Material World

38 Supreme with high and homogeneous hardness as well as pattern guaranteed has longer life time & harder than conventional products.

ENGINEERED BY YUKSELEN




Shapes & Sizes



Rounds

Rolled 10 - 200 mm



Flats

Plate 20 - 150 mm x 1,000 - 1,200 mm
Block 150 - 800 x 1,000 - 1,200 mm


Chemical Composition

38 SUPREME	DIN			Standart			Teslimat Sertliđi			Isıl İşlem Sonrası
	C	Si	Mn	P	S	Cr	Mo	Ni	V	50 - 52 HRc
										1.2738 QT
min	0,22	0,00	1,30	0,00	0,00	1,20	0,45	0,90	0,08	T.Sertliđi (1) 35-39 HRc
max	0,30	0,30	1,60	0,02	0,008	1,30	0,55	1,20	0,12	T.Sertliđi (2) 330-364 HB

Plastic Mold Steel Grades

1.2738 QT / High Hard / DIN 40CrMnNiMo 8-6-4

1.2738 QT/HH QT




Shapes & Sizes



Rounds

Rolled 10 - 180 mm



Flats

Plate 20 - 150 x 1,000 - 2,000 mm
Block 150 - 800 x 1,000 - 2,000 mm

Chemical Composition

1.2738 QT	DIN			Standart			Teslimat Sertliđi	Isıl İşlem Sonrası	
	40CrMnNiMo8-6-4			DIN 17350			max. 302 HB	50 - 52 HRc	
	C	Si	Mn	P	S	Cr	Mo	Ni	
min	0,35	0,20	1,30	0,00	0,00	1,80	0,15	0,90	
max	0,45	0,40	1,60	0,035	0,035	2,10	0,25	1,20	
								T.Sertliđi (1) 28-34 HRc	1.2738 QT
								T.Sertliđi (2) 330-364 HB	

1.2738 HH QT	DIN			Standart			Teslimat Sertliđi	Isıl İşlem Sonrası	
	40CrMnNiMo8-6-4			DIN 17350			35-39 HRc	50 - 52 HRc	
	C	Si	Mn	P	S	Cr	Mo	Ni	
min	0,35	0,20	1,30	0,00	0,00	1,80	0,15	0,90	
max	0,45	0,40	1,60	0,035	0,03	2,10	0,25	1,20	
								T. Sertliđi (1) 35-39 HRc	1.2738 QT
								T. Sertliđi (2) 330-364 HB	

Plastic Mold Steel Grades

1.2312 QT

1.2312 QT / DIN 40CrMnMoS86




Shapes & Sizes



Rounds

Rolled 10 - 200 mm




Flats

Plate 20 - 150 x 1,000 - 2,000 mm
Block 150 - 800 x 1,000 - 2,000 mm

Chemical Composition

1.2312 QT	DIN			Standart				Teslimat Sertliđi	Isıl İşlem Sonrası
	40CrMnMoS 8 6			DIN 17350				max. 230 HB	50 - 52 HRc
	C	Si	Mn	P	S	Cr	Mo		1.2312 QT
min	0,35	0,30	1,40	0,00	0,05	1,80	0,15		Teslimat Sertliđi
max	0,45	0,50	1,60	0,03	0,10	2,00	0,25		28 - 34 HRc



YÜKSELEN

444 20 50 // yuksele.com

MERKEZ (ESENYURT) //

Osmangazi Mahallesi
2647. Sokak No: 40/1
34538 Esenyurt, İstanbul
T: 444 20 50

DUDULLU ŞUBESİ //

Dudullu OSB, DES San. Sit.
1. Cd. Tic. Merkezi No: 3/37
34775 Ümraniye, İstanbul
T: (216) 593 32 32

İZMİR (EGE) ŞUBESİ //

Atatürk Org. San. Bölğ.
10022. Sk. No: 18
35580 Çiğli, İzmir
T: (232) 600 03 03

YÖNETİM (ATAKÖY ŞUBESİ) //

Ataköy Towers A Blok Kat 10
No: 142 Ataköy E-5 Yanyol
34158 Bakırköy, İstanbul
T: (212) 661 89 89

DİLOVASI ŞUBESİ //

Kocaeli Kobi OSB
Köseler Mah. 4. Cd. No: 19
41455 Dilovası, Kocaeli
T: 444 20 50

EXPORT OFFICE //

Avrupa Konutları A-Ofis Kat 6
No: 23 Ataköy E-5 Yanyol
34158 Bakırköy, İstanbul
T: (212) 661 11 57